



UDI Barcode  
Asset Identification



Permanent  
Signage




Medical Device  
Control Panels

THE TECHNOLOGY:

ANODIZED LAYER

The glass-clear, sapphire-hard anodized layer resists chemicals, paint, abrasion and dirt.



ALUMINUM LAYER  
The rigid aluminum base won't peel, crack or delaminate.

SEALED IMAGE  
The image is absorbed into the pores.

EXCEPTIONALLY DURABLE.  
WIDELY SPECIFIED.  
ALWAYS READABLE.

Anodized aluminum has long been a standard for sterilization containers, control panels and other identification products in the surgical field. Metalphoto photosensitive anodized aluminum improves that standard by being resistant to heat, chemicals and harsh cleaning solvents. Ideal for sterile environments, Metalphoto does not harbor bacteria or corrode after thousands of sterilization cleaning cycles.

Metalphoto complies with several medical labeling requirements including AAMI/CDV-1 ST79:2010/A2.06, a comprehensive guide to steam sterilization and sterility assurance, and the FDA Amendments Act of 2007 for the establishment of a Unique Device Identification (UDI) System.

Metalphoto of Cincinnati has been a leading full-service manufacturer of durable custom identification products for more than 50 years. Contact MPC for the best solution to your equipment identification needs.

PRODUCT BENEFITS

EXCEPTIONALLY DURABLE:


- + UV-stable image is permanently sealed within the anodized aluminum.
- + Virtually impervious to chemicals, heat, abrasion, salt spray and sunlight.
- + Certified for 20 year plus outdoor applications.
- + Earned more top scores than any other IUID barcode label material tested by the U.S. Navy (NSWC, Corona Division, IUID Center; August 2011).


WIDELY SPECIFIED:


- + Meets a wide array of commercial, government and military specifications.
- + Notable certifications include: MIL-STD-130N, STANAG 2290, GGP-455B(3) Type I, MIL-DTL-15024F, MIL-P-19834B and A-A-50271 (several others listed on metalphoto.com).


PHOTOGRAPHIC RESOLUTION:


- + Photographic image affords extreme detail and contrast at any size.
- + Anti-counterfeit security printing is available.

 UV STABLE

 ABRASION RESISTANT

 TEMPERATURE RESISTANT

 FLUID RESISTANT

 RECYCLABLE

PERFORMANCE CHARACTERISTICS

Because of its ability to perform across a range of challenging environments, Metalphoto meets an array of government, industrial and military specifications. Visit [www.metalphoto.com](http://www.metalphoto.com) for a list of specifications for which Metalphoto is qualified.

CHARACTERISTIC	RESULT
<b>Abrasion Resistance</b>	No pronounced image loss, degradation or reduced readability after 7,000 cycles on an abrading wheel.
<b>Acid Corrosion</b>	No deterioration or image degradation after 24 hours in 3% nitric acid.
<b>Heat Resistance</b>	No legibility loss or degradation when subjected to 1,000°F.
<b>Salt Spray Corrosion</b>	No deleterious effect after a 720-hr salt spray (fog) test. 2,6 "Very Good" corrosion resistance after 113 days seawater exposure.
<b>Accelerated Light and Weather Resistance</b>	No pronounced deterioration of legibility after 400-hr carbon arc weatherometer exposure. (≈ 20+ year outdoor life)
<b>Accelerated Oxygen Aging</b>	No discoloration or fading after 96-hr/300 psi/ 70°C oxygen bomb aging
<b>Stain Resistance</b>	No black fading when plates are exposed to tincture of iodine.
<b>Cleaning Resistance</b>	No deleterious effects when tested with alkaline cleaners (MILC- 87937 or equivalent) for aircraft surfaces.
<b>Low Temperature Resistance</b>	No deleterious effect or image fade after 1 hour at -50°F. No impairment of legibility upon exposure at -67°F.
<b>Organic Solvent Resistance</b>	No softening, staining or noticeable fade after 24-hr exposure to: JP-4 fuel, Gasoline, Mineral Spirits, Methyl Ethyl Ketone, Turpentine, Turbine & Jet Fuel, Kerosene, Xylo, Acetone, Toluol, Heptane, Trichlorethylene, MIL-H-5606 Hydraulic Fluid and MIL-L-7808 Jet Engine Oil.
<b>Fungus Resistance</b>	Visual reading of "0" per ASTM-G21.
<b>Thermal Shock</b>	No deterioration after 3 cycles between -65°C and 125°C
<b>Moisture Resistance</b>	No deterioration after 10 humidity cycles per MIL-STD-202, method 106.

TECHNICAL SPECIFICATIONS

**MATERIAL:** Anodized Aluminum

**SIZES:** Up to 24" x 40"

**THICKNESSES:** .003", .005", .008", .012", .020", .032", .039", .063", .090", .125"

**FINISHES:**



**MATTE**  
non-reflective  
with dull finish



**SATIN**  
semi-gloss medium  
reflective material



**# 4**  
brushed to resemble  
a stainless steel finish



**GLOSS**  
highly reflective,  
mirror-like

CONTACT MPC

Call **1-800-528-4058** or visit our website at **MPofCinci.com**

\*Metalphoto of Cincinnati does not warrant the performance of its materials in any environment.  
Metalphoto is a registered trademark of Horizons Incorporated.

Ver. 1.0 APRIL 2014



Metalphoto of Cincinnati

1080 Skillman Drive  
Cincinnati, OH 45215

T: 1-800-482-7758  
F: 216-475-6507

E: [cincics@mpofcinci.com](mailto:cincics@mpofcinci.com)  
[www.mpofcinci.com](http://www.mpofcinci.com)